



**TYPICAL PROPERTIES OF
RE43E**

POLYMER

EPDM BLEND

SPECIFICATIONS

ASTM D 1056-67.....	SCE43
ASTM D 1056-78.....	RE43
ASTM D 1056-07.....	2A3
MIL-R-6130C TY/GR/CONDITION.....	II-A MED
MIL-C-3133C MIL STD 670 B.....	SCE11

FLAMMABILITY SPECIFICATIONS

FMVSS-302.....	PASS
----------------	------

PHYSICAL PROPERTY	TEST METHOD	UNIT OF MEASURE	RESULT
COMPRESSION DEFLECTION @25%	ASTM D1056	psi kPa	9-13 62-90
DENSITY	ASTM D1056	pcf g/cm ³	7-11 .112-.176
WATER ABSORPTION MAX. WEIGHT CHANGE	ASTM D1056	%	5
TEMPERATURE RANGE	ASTM D746	°F	-40 TO +200
HIGH INTERMITTENT	ASTM D746	°F	+250
TENSILE STRENGTH TYPICAL	ASTM D412 (DIE A)	psi kPa	100 690
ELONGATION TYPICAL	ASTM D412 (DIE A)	%	125
HEAT AGING (7 DAYS-158°F) CHANGE IN COMP. DEFL	ASTM D1056	180° BEND	±30
THERMAL CONDUCTIVITY	ASTM C177-85	K FACTOR	.30
COLOR	N/A	N/A	BLACK

RESISTANCE TO:			
ACID	EXCELLENT	OZONE	EXCELLENT
ALKALI	EXCELLENT	KETONES	FAIR
GASOLINE AND OIL	POOR	CHLORINATED SOLVENTS	POOR
AROMATIC HYDROCARBONS	FAIR	OXIDATION	EXCELLENT

Marian Inc. | 1011 E. Saint Clair Street | Indianapolis, IN 46202
sales@marianinc.com | 1-800-773-0062 | sales@marianinc.com